

H.P. WHITE LABORATORY, INC.

3414 Scarboro Road
Street, Maryland 21154-1822
Telephone: (410) 838-6550
Facsimile: (410) 838-2802
Email: info@hpwhite.com
www.hpwhite.com



22 February 2007
(HPWLI 10456-01B)

Fromm Barriers, Inc.
P.O. Box 266
Shamokin, PA 17872

Attention: Mr. Jeff Fromm

Gentlemen:

In accordance with your instructions, H.P. White Laboratory, Inc. conducted ballistic resistance testing of one arrayed steel sample received 22 February 2007 via your representatives.

Testing was conducted in accordance with your instructions, and the modified provisions of NIJ-STD-0108.01, BALLISTIC RESISTANT PROTECTIVE MATERIALS, dated September 1985, using caliber 7.62x51mm, 150 grain, M61, AP ammunition supplied by your office. The test sample was rigidly fixtured on an indoor range 50.0 feet from the muzzle of a test barrel to produce zero degree obliquity impacts. Photoelectric lumiline screens were positioned at 6.5 and 9.5 feet which, in conjunction with elapsed time counters (chronographs), were used to compute projectile velocities 8.0 feet forward of the muzzle. Penetrations were determined by visual examination of a 0.020-inch thickness alloy 2024T3 aluminum witness panel positioned 6.0 inches behind, and parallel to, the test sample. Table I presents a summary of the attached data record.

TABLE I. SUMMARY OF RESULTS

Test Sample		Ballistic Threat			Results	
Number	Size (in)	Caliber	Shots	Velocity (fps)		Penetrations
				Maximum	Minimum	
RDB 54 (M61)	33 x 24 x 2.5	7.62, M61	1(a)	2820		0


(a) One impact at location specified by client.

This report is based on data obtained from having tested only the sample submitted, and should NOT be interpreted as an endorsement by H.P. White Laboratory, Inc. of the continuing quality, or performance, of any other items of the same, or similar, design.

The test sample was returned to the custody of your representative. Should you have any questions regarding this matter, or if we may be of any further service, please do not hesitate to contact us.

Very truly yours,

H.P. White Laboratory, Inc.


Craig B. Dunn

CBD/tc
Enclosure